

627 RIVERBANK DRIVE  
GENEVA, IL 60134  
630-232-0104

## Test Report

[www.riverbankacoustics.com](http://www.riverbankacoustics.com)

FOUNDED 1918 BY  
WALLACE CLEMENT SABINE

SPONSOR: **Moxie Surfaces**  
Encinitas, CA

**Sound Absorption**  
**RAL™-A24-156**

CONDUCTED: 2024-03-20

Page 1 of 10

ON: AIR-board Acoustic Quiet – 3/4” (Type F-100 Mounting)

### TEST METHODOLOGY

Riverbank Acoustical Laboratories™ is accredited by the U.S. Department of Commerce, National Institute of Standards and Technology (NIST) under the National Voluntary Laboratory Accreditation Program (NVLAP) as an ISO 17025:2017 Laboratory (NVLAP Lab Code: 100227-0) and for this test procedure. The test reported in this document conformed explicitly with ASTM C423-23: "Standard Test Method for Sound Absorption and Sound Absorption Coefficients by the Reverberation Room Method." The specimen mounting was performed according to ASTM E795-23: "Standard Practices for Mounting Test Specimens During Sound Absorption Tests." A description of the measurement procedure and room specifications are available upon request. The results presented in this report apply to the sample as received from the test sponsor.

### INFORMATION PROVIDED BY SPONSOR

The test specimen was designated by the sponsor as AIR-board Acoustic Quiet – 3/4”. The following nominal product information was provided by the sponsor prior to testing. The accuracy of such sponsor-provided information can affect the validity of the test results.

#### **Product Under Test**

---

Product Name: AIR-board Acoustic Quiet – 3/4”  
Manufacturer: Design Composite  
US Distributor: Moxie Surfaces

### SPECIMEN MEASUREMENTS & TEST CONDITIONS

Through a full external visual inspection performed on the test specimen, Riverbank personnel verified the following information:

#### **Test Specimen**

---

Material: Panels with honeycomb core, microperforated sheet on one side, solid sheet on other side  
Dimensions: 2 panels @ 1219 mm (48 in.) by 2438 mm (96 in.)  
Thickness: 20.13 mm (0.7925 in.)  
Overall Weight: 28.8 kg (63.5 lbs)

627 RIVERBANK DRIVE  
GENEVA, IL 60134  
630-232-0104

## Test Report

[www.riverbankacoustics.com](http://www.riverbankacoustics.com)

FOUNDED 1918 BY  
WALLACE CLEMENT SABINE

**Moxie Surfaces**  
2024-03-20

**RAL™-A24-156**  
Page 2 of 10

### Overall Specimen Properties

Size: 2.44 m (96.0 in) wide by 2.44 m (96.0 in) long  
Thickness: 0.02 m (0.7925 in)  
Weight: 28.8 kg (63.5 lbs)  
Mass per Unit Area: 4.84 kg/m<sup>2</sup> (0.99 lbs/ft<sup>2</sup>)  
Calculation Area: 5.946 m<sup>2</sup> (64. ft<sup>2</sup>)

### Test Environment

Room Volume: 291.98 m<sup>3</sup>  
Temperature: 21.3 °C ± 0.0 °C (Requirement: ≥ 10 °C and ≤ 5 °C change)  
Relative Humidity: 59.2 % ± 0.8 % (Requirement: ≥ 40 % and ≤ 5 % change)  
Barometric Pressure: 99.0 kPa (Requirement not defined)

### MOUNTING METHOD

Type F-100 Mounting: The test specimen was laid over wood spacers placed on the horizontal test surface, creating a 102 mm (4 in.) thick airspace between the test surface and the panel body. The numeral suffix in the mounting designation is the thickness of the spacers in millimeters, rounded to the nearest integer multiple of 5. Perimeter edges were sealed with wood and metal framing and tape.

627 RIVERBANK DRIVE  
GENEVA, IL 60134  
630-232-0104

**Test Report**

[www.riverbankacoustics.com](http://www.riverbankacoustics.com)

FOUNDED 1918 BY  
WALLACE CLEMENT SABINE

**Moxie Surfaces**  
2024-03-20

**RAL™-A24-156**

Page 3 of 10




Figure 1 – Specimen mounted in test chamber



Figure 2 – Individual specimen panel

627 RIVERBANK DRIVE  
GENEVA, IL 60134  
630-232-0104

## Test Report

[www.riverbankacoustics.com](http://www.riverbankacoustics.com)

FOUNDED 1918 BY  
WALLACE CLEMENT SABINE

**Moxie Surfaces**  
2024-03-20

**RAL™-A24-156**

Page 4 of 10




Figure 3 – Wood spacers in test chamber




Figure 4 – Specimen partially installed over spacers

627 RIVERBANK DRIVE  
GENEVA, IL 60134  
630-232-0104

**Test Report**

[www.riverbankacoustics.com](http://www.riverbankacoustics.com)

FOUNDED 1918 BY  
WALLACE CLEMENT SABINE

**Moxie Surfaces**  
2024-03-20

**RAL™-A24-156**  
Page 5 of 10



Figure 5 – Detail of specimen materials

627 RIVERBANK DRIVE  
 GENEVA, IL 60134  
 630-232-0104

## Test Report

[www.riverbankacoustics.com](http://www.riverbankacoustics.com)

FOUNDED 1918 BY  
 WALLACE CLEMENT SABINE

**Moxie Surfaces**  
 2024-03-20

**RAL™-A24-156**  
 Page 6 of 10

### TEST RESULTS

Specimen total absorption and absorption coefficient are tabulated at the eighteen standard frequencies. A graphic presentation of the data and additional information appear on the following pages.

1/3 Octave Center Frequency (Hz)	Total Absorption (m <sup>2</sup> )	Total Absorption (Sabins)	Absorption Coefficient
100	2.72	29.33	0.46
** 125	2.77	29.84	0.47
160	1.69	18.23	0.28
200	1.53	16.43	0.26
** 250	1.35	14.53	0.23
315	0.93	10.02	0.16
400	0.89	9.54	0.15
** 500	0.83	8.95	0.14
630	0.98	10.56	0.17
800	1.24	13.31	0.21
** 1000	1.57	16.85	0.26
1250	2.13	22.93	0.36
1600	2.42	26.07	0.41
** 2000	2.78	29.92	0.47
2500	3.05	32.85	0.51
3150	3.02	32.50	0.51
** 4000	2.29	24.63	0.38
5000	1.47	15.85	0.25

**SAA = 0.28**  
**NRC = 0.30**

627 RIVERBANK DRIVE  
GENEVA, IL 60134  
630-232-0104

## Test Report

[www.riverbankacoustics.com](http://www.riverbankacoustics.com)

FOUNDED 1918 BY  
WALLACE CLEMENT SABINE

**Moxie Surfaces**  
2024-03-20

**RAL™-A24-156**  
Page 7 of 10


### TEST RESULTS (continued)

The sound absorption average (SAA) is defined in ASTM C423-23 Section 3.1.1 as the arithmetic average of the sound absorption coefficients of a material for the twelve one-third octave bands from 200 Hz through 2500 Hz, inclusive, rounded to the nearest integer multiple of 0.01.

The noise reduction coefficient (NRC) is defined from previous versions of ASTM C423 as the arithmetic average of the sound absorption coefficients at 250 Hz, 500 Hz, 1000 Hz, and 2000 Hz, rounded to the nearest integer multiple of 0.05.

Tested by   
\_\_\_\_\_  
Marc Sciaky  
Senior Experimentalist

Report by   
\_\_\_\_\_  
Keith Kimberling  
Test Engineer

Approved by   
\_\_\_\_\_  
Eric P. Wolfram  
Laboratory Manager

627 RIVERBANK DRIVE  
GENEVA, IL 60134  
630-232-0104

## Test Report

[www.riverbankacoustics.com](http://www.riverbankacoustics.com)

FOUNDED 1918 BY  
WALLACE CLEMENT SABINE


Moxie Surfaces  
2024-03-20

**RAL™-A24-156**

Page 8 of 10

### SOUND ABSORPTION REPORT

AIR-board Acoustic Quiet – 3/4"



**SAA = 0.28**

**NRC = 0.30**



RIVERBANK ACOUSTICAL LABORATORIES IS ACCREDITED BY NVLAP (LAB CODE 100227-0) FOR ACOUSTICAL TESTING SERVICES IN ACCORDANCE WITH ISO/IEC 17025:2017 AND FOR THIS PROCEDURE. THIS REPORT MUST NOT BE USED BY THE CLIENT TO CLAIM PRODUCT CERTIFICATION, APPROVAL, OR ENDORSEMENT BY RAL, NVLAP, NIST, OR ANY AGENCY OF THE U.S. GOVERNMENT. THIS REPORT SHALL NOT BE MODIFIED WITHOUT THE WRITTEN APPROVAL OF RAL. THE RESULTS REPORTED APPLY ONLY TO THE SPECIFIC SAMPLE SUBMITTED FOR TESTING; RAL ASSUMES NO RESPONSIBILITY FOR THE PERFORMANCE OF ANY OTHER SAMPLE.



627 RIVERBANK DRIVE  
 GENEVA, IL 60134  
 630-232-0104

## Test Report

[www.riverbankacoustics.com](http://www.riverbankacoustics.com)

FOUNDED 1918 BY  
 WALLACE CLEMENT SABINE

**Moxie Surfaces**  
 2024-03-20

**RAL™-A24-156**  
 Page 9 of 10

### APPENDIX A: Extended Frequency Range Data

Specimen: AIR-board Acoustic Quiet – 3/4” (See Full Report)

*The following non-accredited data were obtained in accordance with ASTM C423-23, but extend beyond the defined frequency range of 100Hz to 5,000Hz. These unofficial results are representative of the RAL test environment only and intended for research & comparison purposes.*

1/3 Octave Band Center Frequency (Hz)	Total Absorption (Sabins)	Absorption Coefficient
31.5	5.88	0.09
40	6.43	0.10
50	4.96	0.08
63	6.69	0.10
80	7.26	0.11
<hr/>		
100	29.33	0.46
125	29.84	0.47
160	18.23	0.28
200	16.43	0.26
250	14.53	0.23
315	10.02	0.16
400	9.54	0.15
500	8.95	0.14
630	10.56	0.17
800	13.31	0.21
1000	16.85	0.26
1250	22.93	0.36
1600	26.07	0.41
2000	29.92	0.47
2500	32.85	0.51
3150	32.50	0.51
4000	24.63	0.38
5000	15.85	0.25
<hr/>		
6300	11.25	0.18
8000	4.80	0.08
10000	-0.87	-0.01
12500	12.79	0.20

627 RIVERBANK DRIVE  
GENEVA, IL 60134  
630-232-0104

## Test Report

[www.riverbankacoustics.com](http://www.riverbankacoustics.com)

FOUNDED 1918 BY  
WALLACE CLEMENT SABINE

**Moxie Surfaces**  
2024-03-20

**RAL™-A24-156**  
Page 10 of 10

### APPENDIX B: Instruments of Traceability

Specimen: AIR-board Acoustic Quiet – 3/4” (See Full Report)

<u>Description</u>	<u>Model</u>	<u>Serial Number</u>	<u>Date of Certification</u>	<u>Calibration Due</u>
System 1	Type 3160-A-042	3160-106968	2023-07-17	2024-07-17
Bruel & Kjaer Mic And Preamp G	Type 4943-B-001	2525858	2023-05-03	2024-05-03
Bruel & Kjaer Pistonphone	Type 4228	2781248	2023-07-12	2024-07-12
EXTECH Hygro 6015	SD700	A.116015	2023-05-31	2024-05-31

### APPENDIX C: Revisions to Original Test Report

Specimen: AIR-board Acoustic Quiet – 3/4” (See Full Report)

<u>Date</u>	<u>Revision</u>
2024-04-08	Original report issued

---

END