627 RIVERBANK DRIVE GENEVA, IL 60134 630-232-0104 Test Report

www.riverbankacoustics.com

FOUNDED 1918 BY WALLACE CLEMENT SABINE

SPONSOR: Moxie Surfaces

Encinitas, CA

Sound Absorption RALTM-A24-158

CONDUCTED: 2024-03-21

Page 1 of 8

ON: AIR-board Acoustic Quiet – 3/4" (Type K Mounting)

TEST METHODOLOGY

Riverbank Acoustical LaboratoriesTM is accredited by the U.S. Department of Commerce, National Institute of Standards and Technology (NIST) under the National Voluntary Laboratory Accreditation Program (NVLAP) as an ISO 17025:2017 Laboratory (NVLAP Lab Code: 100227-0) and for this test procedure. The test reported in this document conformed explicitly with ASTM C423-23: "Standard Test Method for Sound Absorption and Sound Absorption Coefficients by the Reverberation Room Method." The specimen mounting was performed according to ASTM E795-23: "Standard Practices for Mounting Test Specimens During Sound Absorption Tests." A description of the measurement procedure and room specifications are available upon request. The results presented in this report apply to the sample as received from the test sponsor.

INFORMATION PROVIDED BY SPONSOR

The test specimen was designated by the sponsor as AIR-board Acoustic Quiet -3/4". The following nominal product information was provided by the sponsor prior to testing. The accuracy of such sponsor-provided information can affect the validity of the test results.

Product Under Test

Product Name: AIR-board Acoustic Quiet – 3/4"

Manufacturer: Design Composite US Distributor: Moxie Surfaces

SPECIMEN MEASUREMENTS & TEST CONDITIONS

Through a full external visual inspection performed on the test specimen, Riverbank personnel verified the following information:

Test Specimen

Material: Panel with honeycomb core, microperforated sheet on one side, solid

sheet on other side

Dimensions: 1219 mm (48 in.) by 2438 mm (96 in.)

Thickness: 20.13 mm (0.7925 in.) Overall Weight: 14.17 kg (31.25 lbs)



® RIVERBANK ACOUSTICAL LABORATORIES IS ACCREDITED BY NVLAP (LAB CODE 100227-0) FOR ACOUSTICAL TESTING SERVICES IN ACCORDANCE WITH ISO/IEC 17025:2017 AND FOR THIS PROCEDURE. THIS REPORT MUST NOT BE USED BY THE CLIENT TO CLAIM PRODUCT CERTIFICATION, APPROVAL, OR ENDORSEMENT BY RAL, NVLAP, NIST, OR ANY AGENCY OF THE U.S. GOVERNMENT. THIS REPORT SHALL NOT BE MODIFIED WITHOUT THE WRITTEN APPROVAL OF RAL. THE RESULTS REPORTED APPLY ONLY TO THE

SPECIFIC SAMPLE SUBMITTED FOR TESTING; RAL ASSUMES NO RESPONSIBILITY FOR THE PERFORMANCE OF ANY OTHER SAMPLE.

627 RIVERBANK DRIVE GENEVA, IL 60134 630-232-0104

Test Report

www.riverbankacoustics.com

FOUNDED 1918 BY WALLACE CLEMENT SABINE

Moxie Surfaces 2024-03-21

RALTM-A24-158 Page 2 of 8

Overall Specimen Properties

Size: 1.22 m (48.0 in) wide by 2.44 m (96.0 in) long

Thickness: 0.02 m (0.7925 in) Weight: 14.17 kg (31.25 lbs)

Mass per Unit Area: 4.77 kg/m² (0.98 lbs/ft²)

Calculation Area: 5.946 m² (64. ft²)

Test Environment


Room Volume: 291.98 m³

Temperature: $21.4 \,^{\circ}\text{C} \pm 0.0 \,^{\circ}\text{C}$ (Requirement: $\geq 10 \,^{\circ}\text{C}$ and $\leq 5 \,^{\circ}\text{C}$ change) Relative Humidity: $60.85 \% \pm 2.9 \%$ (Requirement: $\geq 40 \%$ and $\leq 5 \%$ change)

Barometric Pressure: 99.8 kPa (Requirement not defined)

MOUNTING METHOD

Type K Mounting: The specimen was placed in the reverberation room in an upright position at an oblique angle to and at least 1.52 m (60 in.) from all walls. Per sponsor request, the perimeter edges were left exposed, as would be typical of a field installation of the product under test.



627 RIVERBANK DRIVE GENEVA, IL 60134 630-232-0104 Test Report

www.riverbankacoustics.com

FOUNDED 1918 BY WALLACE CLEMENT SABINE

RALTM-A24-158

Page 3 of 8


Moxie Surfaces 2024-03-21













TESTING

NVLAP LAB CODE 100227-0

® RIVERBANK ACOUSTICAL LABORATORIES IS ACCREDITED BY NVLAP (LAB CODE 100227-0) FOR ACOUSTICAL TESTING SERVICES IN ACCORDANCE WITH ISO/IEC 17025:2017 AND FOR THIS PROCEDURE. THIS REPORT MUST NOT BE USED BY THE CLIENT TO CLAIM PRODUCT CERTIFICATION, APPROVAL, OR ENDORSEMENT BY RAL, NVLAP, NIST, OR ANY AGENCY OF THE U.S. GOVERNMENT. THIS REPORT SHALL NOT BE MODIFIED WITHOUT THE WRITTEN APPROVAL OF RAL. THE RESULTS REPORTED APPLY ONLY TO THE

SPECIFIC SAMPLE SUBMITTED FOR TESTING; RAL ASSUMES NO RESPONSIBILITY FOR THE PERFORMANCE OF ANY OTHER SAMPLE.

627 RIVERBANK DRIVE GENEVA, IL 60134 630-232-0104 Test Report

www.riverbankacoustics.com

FOUNDED 1918 BY WALLACE CLEMENT SABINE

RALTM-A24-158
Page 4 of 8

Moxie Surfaces 2024-03-21

TEST RESULTS

Specimen total absorption and absorption coefficient are tabulated at the eighteen standard frequencies. A graphic presentation of the data and additional information appear on the following pages.

1/3 Octave Center			
Frequency	Total Absorption	Total Absorption	Absorption
(Hz)	(m^2)	(Sabins)	Coefficient
100	0.41	4.41	0.07
100	-0.41	-4.41	-0.07
** 125	-0.11	-1.18	-0.02
160	0.13	1.38	0.02
200	0.10	1.04	0.02
** 250	0.24	2.60	0.04
315	0.20	2.17	0.03
400	0.24	2.54	0.04
400	0.24	2.54	0.04
** 500	0.21	2.28	0.04
630	0.24	2.60	0.04
800	0.48	5.21	0.08
** 1000	0.80	8.60	0.13
1250	1.26	13.61	0.21
1600	1.43	15.43	0.24
** 2000	1.61	17.32	0.27
2500	1.59	17.16	0.27
3150	1.43	15.37	0.24
** 4000	1.35	14.49	0.23
5000	1.21	13.06	0.20

SAA = 0.12NRC = 0.10



627 RIVERBANK DRIVE GENEVA, IL 60134 630-232-0104 Test Report

www.riverbankacoustics.com

FOUNDED 1918 BY WALLACE CLEMENT SABINE

RALTM-A24-158

Page 5 of 8

Moxie Surfaces 2024-03-21

TEST RESULTS (continued)

The sound absorption average (SAA) is defined in ASTM C423-23 Section 3.1.1 as the arithmetic average of the sound absorption coefficients of a material for the twelve one-third octave bands from 200 Hz through 2500 Hz, inclusive, rounded to the nearest integer multiple of 0.01.

The noise reduction coefficient (NRC) is defined from previous versions of ASTM C423 as the arithmetic average of the sound absorption coefficients at 250 Hz, 500 Hz, 1000 Hz, and 2000 Hz, rounded to the nearest integer multiple of 0.05.

Tested by

Marc Sciaky

Senior Experimentalist

Report by

Keith Kimberlin

Test Engineer

Approved by

Eric P. Wolfram

Laboratory Manager

SPECIFIC SAMPLE SUBMITTED FOR TESTING; RAL ASSUMES NO RESPONSIBILITY FOR THE PERFORMANCE OF ANY OTHER SAMPLE.

627 RIVERBANK DRIVE GENEVA, IL 60134 630-232-0104

Test Report

www.riverbankacoustics.com

FOUNDED 1918 BY WALLACE CLEMENT SABINE


RALTM-A24-158

Page 6 of 8

Moxie Surfaces 2024-03-21

SOUND ABSORPTION REPORT

AIR-board Acoustic Quiet – 3/4"



SAA = 0.12

NRC = 0.10



® RIVERBANK ACOUSTICAL LABORATORIES IS ACCREDITED BY NYLAP (LAB CODE 100227-0) FOR ACOUSTICAL TESTING SERVICES IN ACCORDANCE WITH ISO/IEC 17025:2017 AND FOR THIS PROCEDURE. THIS REPORT MUST NOT BE USED BY THE CLIENT TO CLAIM PRODUCT CERTIFICATION, APPROVAL, OR ENDORSEMENT BY RAL, NVLAP, NIST, OR ANY AGENCY OF THE U.S. GOVERNMENT.

THIS REPORT SHALL NOT BE MODIFIED WITHOUT THE WRITTEN APPROVAL OF RAL. THE RESULTS REPORTED APPLY ONLY TO THE SPECIFIC SAMPLE SUBMITTED FOR TESTING; RAL ASSUMES NO RESPONSIBILITY FOR THE PERFORMANCE OF ANY OTHER SAMPLE.

627 RIVERBANK DRIVE GENEVA, IL 60134 630-232-0104 Test Report

www.riverbankacoustics.com

FOUNDED 1918 BY WALLACE CLEMENT SABINE

Moxie Surfaces 2024-03-21

RALTM-A24-158
Page 7 of 8

APPENDIX A: Extended Frequency Range Data

Specimen: AIR-board Acoustic Quiet – 3/4" (See Full Report)

The following non-accredited data were obtained in accordance with ASTM C423-23, but extend beyond the defined frequency range of 100Hz to 5,000Hz. These unofficial results are representative of the RAL test environment only and intended for research & comparison purposes.

Total Absorption	Absorption
(Sabins)	Coefficient
	-0.03
-0.75	-0.01
	-0.17
-8.92	-0.14
3.05	0.05
-4.41	-0.07
-1.18	-0.02
1.38	0.02
1.04	0.02
2.60	0.04
2.17	0.03
2.54	0.04
2.28	0.04
2.60	0.04
5.21	0.08
8.60	0.13
13.61	0.21
15.43	0.24
17.32	0.27
17.16	0.27
15.37	0.24
14.49	0.23
13.06	0.20
11.38	0.18
11.51	0.18
11.52	0.18
27.72	0.43
	(Sabins) -2.16 -0.75 -10.65 -8.92 3.05 -4.41 -1.18 1.38 1.04 2.60 2.17 2.54 2.28 2.60 5.21 8.60 13.61 15.43 17.32 17.16 15.37 14.49 13.06 11.38 11.51 11.52



® RIVERBANK ACOUSTICAL LABORATORIES IS ACCREDITED BY NVLAP (LAB CODE 100227-0) FOR ACOUSTICAL TESTING SERVICES IN ACCORDANCE WITH ISO/IEC 17025:2017 AND FOR THIS PROCEDURE. THIS REPORT MUST NOT BE USED BY THE CLIENT TO CLAIM PRODUCT CERTIFICATION, APPROVAL, OR ENDORSEMENT BY RAL, NVLAP, NIST, OR ANY AGENCY OF THE U.S. GOVERNMENT.

THIS REPORT SHALL NOT BE MODIFIED WITHOUT THE WRITTEN APPROVAL OF RAL. THE RESULTS REPORTED APPLY ONLY TO THE SPECIFIC SAMPLE SUBMITTED FOR TESTING; RAL ASSUMES NO RESPONSIBILITY FOR THE PERFORMANCE OF ANY OTHER SAMPLE.

627 RIVERBANK DRIVE GENEVA, IL 60134 630-232-0104 Test Report

www.riverbankacoustics.com

FOUNDED 1918 BY WALLACE CLEMENT SABINE

Moxie Surfaces 2024-03-21

RALTM-A24-158

Page 8 of 8

APPENDIX B: Instruments of Traceability

Specimen: AIR-board Acoustic Quiet – 3/4" (See Full Report)

		Serial	Date of	Calibration
Description	Model	Number	Certification	Due
System 1	Type 3160-A-042	3160- 106968	2023-07-17	2024-07-17
Bruel & Kjaer Mic And Preamp G	Type 4943-B-001	2525858	2023-05-03	2024-05-03
Bruel & Kjaer Pistonphone	Type 4228	2781248	2023-07-12	2024-07-12
EXTECH Hygro 6015	SD700	A.116015	2023-05-31	2024-05-31

APPENDIX C: Revisions to Original Test Report

Specimen: AIR-board Acoustic Quiet – 3/4" (See Full Report)

<u>Date</u> <u>Revision</u>

2024-04-08 Original report issued

END

